



KÖSTER TPO Cleaner

Cleaner for KÖSTER TPO - Roofing Membranes

Features

Cleaner for preparing the seam area of KÖSTER TPO roofing membranes in case of heavy soiling or after weathering.

Technical Data

Material	Solvent mixture based on aliphatic and aromatic hydrocarbons
Color	colorless
Minimum processing temperature	> + 5 °C
Flashpoint	- 20 °C
Boiling point	+ 69 °C
Density	0.7 g / cm ³
Flash-off time (at + 15 °C)	approx. 5 minutes
Minimum durability	24 months

Fields of Application

Cleaner for the seam area of KÖSTER TPO - Roofing Membranes

Application

KÖSTER TPO Cleaner is applied with a cleaning cloth over the whole surface of the soiled area and then wiped dry. In case of heavy soiling, wipe with a fresh cloth. Before welding the roofing membranes, the cleaner must be allowed to completely flash off.

The application of KÖSTER TPO Roofing and Waterproofing Membranes is carried out according to the installation instructions and the technical manual of the KÖSTER BAUCHEMIE AG.

Consumption

ca. 0.01 - 0.03 l pro m

Packaging

RT 105 002 2.5 l jerrycan

Storage

Store in a closed and cool place. Close container after use. Do not overheat!

Safety

Observe KÖSTER Safety Data Sheet!

Fire behavior: highly flammable

Health hazard: irritant

Observe all local, federal, and state regulations when processing the material.

Related products

KÖSTER TPO Cleaning Tissue

Prod. code RT 105 003

KÖSTER TPO Pro 1.5

Prod. code RT 815 150 Pro

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.